



Specialty Flooring Products

www.nikkacorp.com | (678) 290-0830

TECHNICAL DATA: POLYASPARTIC COATING

Polyaspartic Coating

NC-Polyaspartic Coating (NC-PAC) is an experimental solvent based two component 66% solids polyaspartic aliphatic urethane clear coating. NC-PAC has excellent chemical resistance, hardness, abrasion resistance, UV stability and has an excellent clear gardner color. However, the outstanding feature of this product is its exceptionally quick tack free time of around 1-2 hours for foot traffic.

Recommended Uses

It is suitable as a thin build coating only.

General Product Data

SOLIDS BY WEIGHT:

66% (+/- 3%)

SOLIDS BY VOLUME:

61% (+/-3%)

VOLATILE ORGANIC CONTENT:

2.81 pounds per gallon

RECOMMENDED FILM THICKNESS / COVERAGE PER GALLON:

2-4 mils wet / 400-800 square feet per gallon

HARDNESS:

Shore D= 80

PACKAGING INFORMATION

2 gallon kit (net approximately)

AVAILABLE COLORS:

Clear – gardner color 1

ABRASION RESISTANCE:

Taber abraser CS-17 calibre wheel with 1000 gram total load and 500 cycles= 21 mg loss

FINISH CHARACTERISTICS:

Gloss (>70 at 60 degrees)

SHELF LIFE:

6 months in unopened containers

VISCOSITY:

<200 centipoise

COMPRESSIVE STRENGTH:

12,000 psi @ ASTM D695

ULTIMATE ELONGATION:

2.4%

TENSILE STRENGTH:

3,900 psi @ ASTM D638

MIX RATIO:

One to one by volume

DOT CLASSIFICATIONS:

Part A "FLAMMABLE LIQUID N.O.S., 3, UN1993, PGIII"

Part B "FLAMMABLE LIQUID N.O.S., 3, UN1993, PGIII"

CURE SCHEDULE (70°) (70% relative humidity):

Pot life – 150 gram mass greater than 1 hour
(actual usable working time is approximately 30 minutes)

Tack free (dry to touch)..... 1-2 hours

Recoat or topcoat..... 2-3 hours

Light foot traffic.....1-4 hours

Full cure (heavy traffic)....24-48 hours

APPLICATION TEMPERATURE:

50-90 degrees F with relative humidity below 85%

CHEMICAL RESISTANCE:

REAGENT	RATING
xylene	3
1,1,1 trichloroethane	2
MEK	1
methanol	2
ethyl alcohol	2
skydrol	3
50% sodium hydroxide	5
10% sulfuric acid	3
10% HCl (aq)	3
5% acetic acid	3

Rating key: 1 - not recommended, 2 - 2 hour term splash spill, 3 - 8 hour term splash spill, 4 - 72 hour immersion, 5 - long term immersion. NOTE: extensive chemical resistance information is available through your sales representative.

PRIMER:

Recommend a suitable primer and testing to determine suitability.

TOPCOAT:

None recommended

LIMITATIONS:

- *As an experimental product, obtain a sample and thoroughly evaluate product before using. Samples are available upon request.
- *Color stability may be affected by environmental conditions like high humidity/chemical exposure. Exposure to some types of lighting such as sodium vapor lights may cause discolorations.
- *Test Data based on neat resin.
- *Clarity of color may vary from batch to batch
- *Substrate temperature must be 5°F above dew point.
- *Too thick of an application may result in surface imperfections, bubble generation or product failure.
- *Always apply a test patch to determine product suitability and adhesion performance for your proposed application method and procedures.
- *All new concrete must be cured for at least 30 days prior to application.
- *Do not expose this product to water until fully cured.
- *See reverse side for application instructions.
- *Physical properties are typical values and not specifications.
- *See reverse side for limitations of our liability and warranty.
- *Relative humidity can affect dry time and gel time – See page 2
- *See reverse side for limitations of our liability and warranty.
- *Relative humidity can affect dry time and gel time – See page 2

Polyaspartic Coating

Mixing and Application Instructions

PRODUCT STORAGE: Store product at normal room temperature before using. Continuous storage should be between 60 and 90 degrees F. Low temperature or temperature fluctuations may cause crystallization

SURFACE PREPARATION: The most suitable surface preparation would be a brush blast (shot blast) to remove all laitance and provide a suitable profile. All dirt, foreign contaminants, oil and laitance must be removed to assure a trouble free bond to the substrate. A test should be made to determine that the concrete is dry; this can be done by placing a 4'X4' plastic sheet on the substrate and taping down the edges. If after 24 hours, the substrate is still dry below the plastic sheet, then the substrate is dry enough to start coating. The plastic sheet testing is also a good method to determine if any hydrostatic pressure problems exist that may later cause disbonding..

PRODUCT MIXING: This product has a mix ratio of one to one by volume. Standard packages are in pre-measured kits and should be mixed as supplied in the kit. After the two parts are combined, mix well with slow speed mixing equipment such as a jiffy mixer until the material is thoroughly mixed and streak free. After mixing, transfer the mixed material to another pail (the transfer pail) and again remix. The material in the transfer pail is now ready to be applied on the properly prepared surface.

PRIMING: A suitable primer should be used before applying this product. However, whether a primer is used or not, it is advisable to apply a test patch prior to using this product to determine if the adhesion characteristics are suitable for the service environment.

PRODUCT APPLICATION: The mixed material can be applied by brush or roller. Maintain temperatures and relative humidity within the recommended ranges during the application and curing process. This product is only intended for use as a thin build topcoat. Improper mixing may result in product failure. It should be pointed out that relative humidity can have a dramatic influence on the curing characteristics. The product will dry quicker and have less working time when the relative humidity is higher while a lower relative humidity will lengthen the dry time and working time.

RECOAT OR TOPCOATING: This material can be applied in multiple coats. If you opt to recoat this product, you must first be sure that the coating has tacked off before recoating. Always remember that colder temperatures will require more cure time for the product before recoating can commence.

CLEANUP: Use xylol

FLOOR CLEANING: Caution! Some cleaners may affect the color of the floor installed. Test each cleaner in a small area, utilizing your cleaning technique. If no ill effects are noted, you can continue to clean with the product and process tested.

RESTRICTIONS: Restrict the use of the floor to light traffic and non-harsh chemicals until the coating is fully cured (see technical data under full cure). It is best to let the floor remain dry for the full cure cycle.

Warranty Statement

We warrant that our products are manufactured to strict quality assurance specifications and that the information supplied by us is accurate to the best of our knowledge. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you shall make your own tests to determine the suitability of our product for your particular purpose. Listed physical properties are typical and should not be construed as specifications. No warranty is made, expressed or implied, regarding such other information, the data on which it is based, or the result you will obtain from its use. No warranty is made, expressed or implied, that our products shall be merchantable or that our product shall be fit for any particular purpose. No warranty is made that the use of such information or our product will not infringe upon any patent. We shall have no liability for incidental or consequential damages, direct or indirect. Our liability is limited to the net selling price of our product or the replacement of our product, at our option. Acceptance of delivery of our product means that you have accepted the terms of this warranty whether or not purchase orders or other documents state terms that vary from this warranty. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Our products contain chemicals that may cause serious physical injury. Before using, read the material safety data sheets and follow all precautions to prevent bodily harm.